INTEGRALE



High pressure decorative laminates (HPL), having thickness 2 mm or greater, according to EN 438-4:2005 or EN 438-8:2005, consisting of a surface of decorative paper(s), on one or both sides, impregnated with aminoplastic resins and a core made of layers of kraft paper impregnated with phenolic thermosetting resins. All the layers are bonded together with simultaneous application of heat (approximately 150°C) and high spec fic pressure (> 7 MPa) to obtain a homogeneous non-porous material with increased density. When these laminates are self-supporting they are ready for installation. They are available in the standard CGS and ATS and in the flame relardant CGF and ATE types.

		CGF and ATF types. Decor		Plain colours	Printed decors	Iridescent colou
		EN 438 classification Standard	-	CGS/CGF EN 438-4	CGS/CGF EN 438-4	ACS/ATF EN 438-8
PROPERTIES	TEST METHOD	PROPERTY OR ATTRIBUTE	UNIT	VALUES		
FACE QUALITY						
ace quality	EN 438-2.4	Spots, dirt and similar surface defects	mm ² /m ²	≤1		
		Fibres, hairs and scratches	mm/m ²		≤ 10	
ENSIONAL TOLERANCES						
Dimensional tolerances		Thickness tolerance	mm mm	2,0 ≤ t < 3,0: ± 0,20 3,0 ≤ t < 5,0: ± 0,30		
	EN 438-2.5		mm mm	5,0 ≤ t < 8,0: ± 0,40 8,0 ≤ t < 12,0: ± 0,50		
	EN 436-2.5		mm mm	12,0 ≤ t < 16,0: ± 0,60 16,0 ≤ t < 20,0: ± 0,70		
			mm mm		20,0 ≤ t < 25,0: ± 0,80 25,0 ≤ t: ± 1,40	
	EN 438-2.6	Length and width	mm	+ 10 / - 0		
	EN 438-2.7	Straightness of edges	mm/m	≤1,5		
	EN 438-2.8		mm/m		≤ 1,5	
	EIN 436-2.0	Squareness			2,0 t < 6,0: ≤ 8	
	EN 438-2.9	Flatness (measured on full-size sheet).	mm/m mm/m mm/m	2,0 ≤ t < 10,0 ≤ 5 6,0 ≤ t < 10,0 ≤ 5 10,0 ≤ t ≤ 3		
			, internet i		10,0 st. s 3	
ERAL PROPERTIES		later Dates	Develor			
istance to surface wear	EN 438-2.10	Initial Point Wear value	Revolutions Revolutions	≥ 150 ≥ 350	≥ 100 ≥ 200	N/A N/A
		Mass increase - 2 ≤ t < 5 mm	%		SeATS≤5,0 - CGFeATF≤	
esistance to immersion in boiling water		Mass increase - 5 ≤ t mm	%	CGS e ATS ≤ 2,0 - CGF e ATF ≤ 3,0		
	EN 438-2.12	Thickness increase - 2 ≤ t < 5 mm Thickness increase - 5 ≤ t mm	%	CGS e ATS ≤ 6,0 - CGF e ATF ≤ 9,0 CGS e ATS ≤ 2,0 - CGF e ATF ≤ 6,0		
		Appearance - Gloss Finish	Rating	≥3		
		Appearance - Other finish	Rating	≥ 3 ≥ 4		
sistance to water vapour	EN 438-2.14	Appearance - Gloss Finish	Rating		≥ 3	
		Appearance - Other finish	Rating		≥ 4	
sistance to dry heat (180°C/20')	EN 438-2.16	Appearance - Gloss Finish Appearance - Other finish	Rating Rating	≥ 3 ≥ 4		N/A N/A
sistance to wet heat (100)	EN 12721:1997	Appearance - Gloss Finish Appearance - Other finish	Rating Rating	≥ 3 ≥ 4		N/A N/A
		Cumulative dimensional change - 2 ≤ t < 5 mm	Longitudinal %	2.4	≤ 0,40	
imensional stability at elevated temperatures	EN 438-2.17	Cumulative dimensional change - 5 ≤ t mm	Longitudinal %	≤ 0,30		
		Cumulative dimensional change - 2 ≤ t < 5 mm Cumulative dimensional change - 5 ≤ t mm	Transversal % Transversal %	≤ 0,80 ≤ 0,60		
istance to impact with large diameter ball	EN 438-2.21	Indentation diameter - $2 \le t < 6$ mm with 1.4 m drop height Indentation diameter - $6 \le t$ mm with 1.8 m drop height	mm mm			h 800 / d ≤ 12 h 800 / d ≤ 12
istance to crazing	EN 438-2.24	Appearance	Rating		≥ 4	
istance to scratching	EN 438-2.25	Appearance - Smooth Finishes Appearance - Textured Finishes	Rating Rating	≥ 2 ≥ 3		≥ 2 ≥ 2
istance to staining	EN 438-2.26	Appearance - Group 1 & 2	Rating		≥ 5	÷
		Appearance - Group 3	Rating		≥ 4	
ht fastness (Xenon-arc)	EN 438-2.27	Contrast	Grey scale rating		≥ 4	
istance to cigarette burns	EN 438-2.30	Appearance	Rating	≥ 3 N/A		
kural modulus	EN ISO 178	Stress	Мра	≥ 9000		
xural strength	EN ISO 178	Stress	Мра	≥ 80		
nsity	EN ISO 1183	Density	g/cm ³	≥ 1,35		
E PERFORMANCES						
		Classification - 2 mm ≤ t < 6 mm	Classification		D-s1,d0 (metal frame)	
Reaction to fire / CGS and ACS types	EN 13501	Classification - t ≥ 2,5 mm	Classification		C-s1,00 (media mane) C-s1,00 (media frame) D-s2,00 (wood frame)	
		Classification - t ≥ 2,5 mm	Classification		D-s2,d0 (wood trame) B-s1,d0 (metal frame)	
	EN 13501	Classification - t \ge 2,5 mm Classification - 3 mm \le t < 6 mm Classification - t \ge 6 mm	Classification Classification Classification	B-s1.d0 (metal frame) C-s2,d0 (metal frame and wood frame) B-s1.d0 (metal frame and wood frame)		
HER PROPERTIES				5-31		
rmal resistance / conductivity	EN 12664	Thermal resistance / conductivity	W/mK		0,2 to 0,5	
ormaldehyde emission	EN 717- 1	Chamber method	mg/m ³ ppm	0,020 - 0,035 0,015 - 0,030		
	EN 717- 2 EN 13986	Gas analysis Classification	mg/(m ² x h) Rating	0,2 - 0,4 E1		
		Individual VOCs	TLV / CA chronic REL		≤ 1/100 / ≤ 1/2	
	GGPS.002 Greenguard Children & School Standard	Formaldehyde TVOC	ppm / ppb		0,0135 / 13,5 ≤ 0.22	
olatile Organic Chemical Emissions	according to US California Dept. of Health Services	Total Aldehydes	mg/m ³ ppm / ppb		0,043 / 43	
	(CA section 01350)	Total Phthalates Total Particles	mg/m ³ mg/m ³	≤ 0,01 ≤ 0,02		
	EN 1186-3	3% acetic acid 24h at 40°C			< 10	
ntact with food - Overall migration	EN 1186-3 EN 1186-14	50% ethanol 24h at 40°C 95% ethanol 24h at 40°C	mg/dm ²	< 10 < 10		
	211 1100-14		1	< 10		
tact with food - Formaldabuda aparitie mis-star	EN 1186-14 EN 12120-22	isooctane 24h at 40°C	mailtra			
tact with food - Formaldehyde specific migration	EN 1186-14 EN 13130-23	Isooctane 24h at 40°C 3% acetic acid 24h at 40°C Microbial growth - Smooth finish Microbial growth - Textured finish	mg/kg Rating		< 15 0 - no microbal growth	

Disclaimer
The Product Technical Sheets provide all the technical information relevant to the performance of the product as tested by Arpa Industriale or certified testing agencies. Arpa Industriale maintains the right to change and alter the product composition and production process and thereby the
performance characteristics of the product at all times, as reported to the Arpa Industriale website. Customers and end-users of the product are requested to check for the latest technical information regarding the product sperformance on the website of Arpa Industriale before application. In
any case, Arpa Industriale, in every contractual relationship, will refer only to the technical information published on its website. Arpa Industriale will not assume any liability if the end-user or customer refer to any other technical information of the products.